

SIGNOLIT® SI 262 power-sol PET film

Description	<i>Material</i>	- clear polyester film with glossy coating on one side
	<i>Coating</i>	- glossy coating
	<i>Properties</i>	- good scratch resistance, non-buckling - brilliant colour reproduction - various applications possible when using white ink
	<i>Application</i>	- for indoor and outdoor
	<i>Durability</i>	- medium-term depending on the ink type
	<i>Inks</i>	- eco-solvent inks - mild-solvent inks - solvent inks - UV curable inks
Examples of use	<i>Indoor and Outdoor</i>	- glass decoration, shop window advertisement - posters, exhibition panels, displays, banner, advertising, signs, - labels, decoration films for film keyboards for machines, etc. In case of a multi-panel presentation it is necessary to check before printing that in regard to the thickness of the film the printer can print with sufficient dimensional accuracy.
Temperature setting:		Before printing it is absolutely necessary to check that the correct drying temperature has been set by carrying out a trial print. Too high drying temperatures can lead to a deformation of the film which can later cause further problems while processing
Drying time / Processing:		The VOC which are contained in solvent inks must be fully dried before further processing. For this reason it is necessary to take long enough drying times into account. The drying time of the printed media depends very much on the quantity of solvent applied. When printing the film in a roll-to-roll process, the printed strip must be unrolled and laid flat as soon as possible until final drying. Solvent residues due to insufficient drying times can lead to blocking during transport in rolled-up form. During lamination such residues can negatively impact the quality of the finished product (flatness, shrinkage behaviour, anchorage, etc...).
Laminating		The printed surface must be protected if it is subject over a long time to humidity, abrasion, sweat or other mechanical influences. In this case the print must be protected with self-adhesive laminating films or appropriate liquid lamination products.

Technical data

<i>Base material</i>	Polyester film clear
<i>Thickness</i>	~ 190 µm
<i>Grammage</i>	~ 280 g/m ²
<i>Dimensions</i>	Rolls 760 mm x 30 m. 914 mm x 30 m. 1067 mm x 30 m. 1270 mm x 30 m. 1370 mm x 30 m. 1520 mm x 30 m.
<i>Core</i>	76 mm

Storage

After printing the remaining roll must be removed from the plotter and stored in its closed original packing in a cool and dry environment.

Disposal

The left-over pieces of film can be treated as industrial waste and incinerated. Nevertheless, it is absolutely necessary to follow the local regulations in force in the waste treatment plants.

Hints

This information corresponds to our present state of knowledge and is destined to inform you without obligation about our products and their use. Our hints and recommendations do not release you from the necessity to ensure by your own tests our product's suitability for its intended use as we do not have any influence on the conditions at your place and on possible influences which may occur during use or application. Due to the large number of combinations of software options, printing profiles, printers, inks, print qualities and resolutions we cannot state exact drying times and the maximum ink quantity required. We reserve the right for any changes useful for product improvement.